



SHEP SELECT NON SAG

NON-SAG JOINT SEALANT

DESCRIPTION

SHEP SELECT NON SAG is an elastic, low-modulus, one-component, moisture-curing, non-sag, polyurethane sealant. It maintains flexibility and waterproofing joint sealing with high bond strength and provides outstanding durability in the civil and industrial construction markets. The product requires no mixing and typically requires no priming to bond to many materials, including concrete and masonry.

USES

SHEP SELECT NON SAG has very good adhesion to most construction materials. It is particularly recommended for expansion joints between precast concrete panels and seams on wooden, aluminum, and PVC joinery. SHEP SELECT NON SAG is highly recommended for bonding concrete and baked clay roof tiles.

FEATURES & BENEFITS

- Ready to use and easy to gun and tool/No mixing and speeds application.
- Low VOC content/Approved in all 50 states for use.
- +/- 35% joint movement capability/Maintains flexibility in moving joints.
- No primer required for most construction materials/Cost reduction.
- Maintains excellent weather resistance/Gives long lasting joint seal.
- Delivers a practical service temperature range/Can be used in all climates.
- Packaged in cartridges, sausages, and in bulk/Jobsite waste is reduced.
- Superior bonding/Long lasting baked clay roof tile application.

PACKAGING

- 10.1 oz. (300 mL) Cartridges (24/Carton)
- 20 oz. (592 mL) Sausages (20/Carton)
- 5 gal. (18.9 L) Pails
- 55 gal. (208.2 L) Drums

AVAILABLE COLORS

Limestone, Stone Gray, Tan, White, Black, and Bronze

COVERAGE

This chart shows the approximate number of lineal feet that can be sealed per gallon. One gallon is approximately 11 cartridges.

Joint Depth	Joint Width						
	1/4" (6.4mm)	3/8" (9.5mm)	1/2" (12.7mm)	5/8" (15.9mm)	3/4" (19.1mm)	7/8" (22.2mm)	1" (25.4mm)
1/4" (6.4mm)	308	205	154	122			
3/8" (9.5mm)				82	68	58	51
1/2" (12.7mm)					51	44	38

When estimating, figure 11 cartridges/gal. (3 cartridges/L).
Cubic in./gal. - 231 (1,000 cm³)
Cubic in./cartridge - 21 (344.13 cm³)

For triangular cross-section joints:

- 1/4" (6.35 mm) each side - 616 linear ft./gal. (49.6 m/L)
- 1/2" (12.7 mm) each side - 154 linear ft./gal. (12.4 m/L)
- 3/4" (19.1 mm) each side - 68 linear ft./gal. (5.5 m/L)

SHELF LIFE

When stored indoors and in original, unopened containers at temperatures between 41° - 104°F (5° - 40°C), shelf life is a minimum of one year from date of manufacture, except for pails and drums, which have a shelf life of six months.

SPECIFICATIONS

- ASTM C 920-11, Type S, Grade NS, Class 35, Use T₁, T₂, NT, O, M, G
- Federal Specification TT-S-00230C, Type II, Class A
- USDA compliant for use in meat and poultry areas
- ISO 11600-F-25LM
- Complies with all current federal, state, and local maximum allowable VOC requirements, including U.S. EPA, LADCO, SCAQMD, and OTC.

MasterFormat:
07 92 13
32 13 73
Revised:
06/15

SHEP SELECT NON SAG

PRODUCT INFORMATION ■ TECHNICAL DATA SHEET

Continued on reverse side

TECHNICAL DATA

Consistency	Thixotropic
Specific Gravity @ 68°F (20°C)	1.27
Paint Compatibility	Water-based: Compatible Solvent-based: Check Compatibility
Skin Formation Time, 74°F (23°C), 50% RH	60-90 minutes
Shore A Hardness	25-30
Sagging (ISO 7390)	None
Modulus at 100% Elongation (ISO 8339), MPa	0.3
Elongation at Break, %	800
Application Temperature	41° - 104° F (5° -40°C)
Service Temperature	-40° -176°F (-40 -80°C)
Substrate Staining	None
Resistance to Weathering	Excellent
UV Resistance	Good
Resistance to Diluted Acids and Bases	Medium
Salt Water Resistance	Excellent
VOC Content	102 g/L

APPLICATION

Surface Preparation: Substrate must be clean, dry, and free of dust and grease. Be sure interfaces are free of curing compounds and/or saw residue.

Application Method: SHEP SELECT NON SAG can be applied with a manual or pneumatic caulking gun. Use typical joint sealing practices and proper joint design of 2:1 width to depth ratio when applying. Horizontal joints require a minimum of 1/4" (6.4 mm) depth and maximum 1/2" (12.7 mm) depth. After application, the product can be smoothed with a damp knife.

Cleanup: Application tools can be cleaned with toluene or xylene before curing. Afterwards, mechanical cleaning will be required.

PRECAUTIONS

Check for compatibility to materials and working techniques not outlined above. SHEP SELECT NON SAG must be fully cured prior to installation of other materials over the product. Do not apply on wet substrates. Do not apply at temperatures outside application temperature range. (See physical properties chart.)

LEED INFORMATION

May help contribute to LEED credits:

- IEQ Credit 4.1: Low Emitting Materials - Adhesives and Sealants
- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

DISCLAIMER

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. We cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As we have no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.