



SHEP WELD PLUS

INTEGRAL BONDING AGENT

DESCRIPTION

Shep Weld Plus is a ready use, film forming, one-time re-emulsifiable liquid bonding agent and polymer modifier for concrete. It may be used inside or outside as a bonding agent admixture for concrete repair, leveling, grouts, thin sets and mortar beds or rubbing applications. Shep Weld Plus is an excellent surface bonder and may be used above or below grade.

PRIMARY APPLICATIONS

Use Shep Weld Plus for concrete patching, topping, underlayments and leveling, overhead repairs, as a bond and strength improving admixture for surface repairs and rubbing mix. Use Shep Weld Plus for plaster, stucco, tuck-pointing, setting tile, tile grout, grout beds and bonding new concrete to old concrete.

FEATURES & BENEFITS

- Use as integral polymer modifier for cement mortars
- Use as a surface bonder
- Not moisture sensitive after use
- Re-emulsifiable one time only
- Not a PVA
- Inside or outside applications
- High solids copolymer emulsion
- VOC Compliant
- Not affected by many freeze-thaw cycles
- Excellent ultra violet light resistance
- Resistance to most petroleum solvents

DIRECTIONS FOR USE

Surface Preparation: All surfaces must be clean and structurally sound, free of curing compounds, sealers, form release agents, oil, grease, paint, etc. Pores of the surface must be open to permit penetration and proper bonding. Necessary surface preparation may be done by abrasive blasting, scarifying or acid etching. If acid etch is used, surface must be neutralized and brushed thoroughly. Rinse and clean thoroughly with clean water.

Application:

Surface Bonder:

- Shake Shep Weld Plus thoroughly before using. Apply Shep Weld Plus directly to the surface in thin uniform coating by brush, roller or spray. Dampen brush or roller and shake out water. Very porous or slick surfaces may require two coats. For two coat applications, apply the second coat at a right angle to the first coat, allowing the first coat to dry in between applications. One gallon of Shep Weld Plus will cover approximately 200 ft². DO NOT apply topping until Shep Weld Plus has completely dried (clear in color). Topping should be applied within 24 hours. DO NOT mix Shep Weld Plus with water for this type of application.

Integral Bonding Agent:

- Once Shep Weld Plus has been used as an integral mix, it will not re-emulsify at all. For specific mix designs, please see chart below. Always do a test section before proceeding.

TECHNICAL DATA

Typical test results of Shep Weld Plus are listed below. Mix design used for these test results is 1 - 2.5 cement (Type I) and sand mix and a 1 : 1 Shep Weld Plus and water ratio (sand used meet ASTM C 33).

Compressive Strength ASTM C 109

7 day (air-cured)	4410 psi
28 day	4880 psi

Flexural Strength ASTM C 78

7 day (air-cured)	1361 psi
28 day	1591 psi

Bond Strength ASTM C 1042*

7 day (air-cured)	710 psi
28 day	890 psi

Commercial Testing Laboratory report available on request.

*A slurry of Shep Weld Plus and cement was used.

Appearance: White in liquid form, clear when dry.

Continued on reverse side

SHEP WELD PLUS

PRODUCT INFORMATION ■ TECHNICAL DATA SHEET

TX/NM

PACKAGING

1 gallon jugs and 5 gallon pails

LIMITATIONS

- Do not use below 45°F. Do not let freeze.

PRECAUTIONS

- Avoid contact with skin and eyes. In case of contact with eyes, flush with cold water for 15 minutes. In case of contact with skin, wash with soap and water. If irritation persists, or if swallowed, call a physician.

LIMITED WARRANTY: NOTICE - READ CAREFULLY. CONDITIONS OF SALE. Manufacturer offers this product for sale subject to, and Buyer and all users are deemed to have accepted, the following conditions of sale and limited warranty which may be varied by written agreement of a duly authorized corporate officer of Manufacturer. No other representative of or for Manufacturer is authorized to grant any warranty or to waive limitation of liability set forth below.

Warranty Limitation: Manufacturer warrants this product to be free of manufacturing defects. If the product when purchased was defective and was within use period indicated on container or carton, when used, Manufacturer will replace the defective product with new product without charge to the purchaser. Manufacturer makes NO OTHER WARRANTY, either expressed or implied, concerning this product. There is NO WARRANTY OF MERCHANTABILITY. In no case shall Manufacturer be liable for special, indirect or consequential damages resulting from the use or handling of the product, and no claim of any kind shall be greater in amount than the purchase price of the product in respect of which damages are claimed.

Inherent Risk: MANUFACTURER MAKES NO WARRANTY TO THE PERFORMANCE OF THE PRODUCT AFTER IT IS APPLIED BY THE PURCHASER, AND PURCHASER ASSUMES ALL RISKS ASSOCIATED WITH THE USE OR APPLICATION OF THE PRODUCT.